

| | | Top Notch | Top Notch 9 | Top Notch 1S | Top Notch FR | Top Gun | Top Gun 9 | Top Gun 1S | Top Gun FR | Top Gun FR Lite | Top Gun Vision | Odyssey | Odyssey FR | Odyssey Open | Softouch | Softouch SD | Amerglo |
|------------------------|---------------------------|------------|-------------|--------------|--------------|---------------|-----------|------------|------------|-----------------|----------------|-----------|------------|--------------|-----------|-------------|-----------|
| Width | in | 60 | 60 | 60 | 60 | 62 & 2 meter* | 62 | 60 | 62 | 62 | 62 & 2 meter | 64 | 64 | 64 | 60 | 60 | 60 |
| Roll Size | yards | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 45 | 50 | 50 | 75 | 100 | 100 | 50 | 50 | 100 |
| Weight | oz/yd ² | 11.5 | 9.0 | 7.5 | 11.5 | 11.5 | 9.0 | 9.0 | 13.0 | 8.0 | 11.0 | 6.5 | 7.25 | 5.75 | 11.0 | 12.5 | 8.25 |
| Tensile Tear | lbf; Warp x Fill | 500+ x 460 | 500+ x 300 | 320 x 255 | 500 x 240 | 500+ x 388 | 360 x 250 | 480 x 340 | 498 x 380 | 275 x 200 | 255 x 150 | 297 x 220 | 300 x 240 | 300 x 215 | 348 x 222 | 368 x 268 | 275 x 195 |
| Tongue Tear | lbf; Warp x Fill | 46 x 38 | 30 x 22 | 29 x 25 | 24 x 14 | 40 x 32 | 30 x 29 | 38 x 30 | 25 x 18 | 12 x 10 | 34 x 15 | 22 x 20 | 12 x 12 | 14.5 x 12 | 36 x 30 | 61 x 54 | 15 x 12 |
| Spray Rating | | 100 | 100 | 100 | 90+ | 90+ | 90+ | 90+ | 90+ | 90+ | n/a | 90+ | 90+ | 80 | 90+ | 100 | n/a |
| 3 Drop | cm | 36 | 40 | 82 | 90 | 76 | 71 | 76 | 70 | 60 | n/a | 51 | 21 | n/a | 84 | 84 | n/a |
| Warranty | years | 8 | 8 | 5 | 8 | 5 | 4 | 5 | 8 | 5 | 5 | 3 | 3 | 3 | 3 | 3 | 3 |
| Breathability | g/m ² /24 hour | 645 | 700 | 260 | 170 | 116 | 100 | 180 | 92 | 78 | 631 | 87 | 86 | 890 | 90 | 96 | 29 |
| Shrinkage | %; Warp x Fill | 0 x 0 | 0 x 0 | <1 x 0 | 0 x 0 | 0 x <1 | 0 x 0 | 0 x 0 | 0 x <1 | <1 x <1 | 0 x 0 | 0 x <1 | 0 x <1 | <1 x <1.25 | <1 x <1 | 0 x 0 | n/a |
| Stretch | %; Warp x Fill | <1 x <1 | <1 x <1 | <1 x <1.5 | <1 x <1 | <1 x <1 | <1 x <1 | <1 x <1 | <1 x <1 | <1 x <1 | 2.5 x 2.5 | <1 x <1 | <1 x <1.25 | <1 x <1.5 | <1 x <1 | <1 x <1 | n/a |
| Taber Abrasion | Cycles till breakthrough | 600+ | 600+ | 1,600+ | 2,000+ | 16,000+ | 10,000+ | 10,000+ | 16,000+ | 2,900+ | 16,000+ | 2,900+ | 2,900+ | 900+ | 13,000+ | 13,000+ | n/a |
| Roll Diameter | in | 7.5 | 7.0 | 6.0 | 7.0 | 7.0 | 6.0 | 6.0 | 6.75 | 5.75 | 7 | 6.5 | 7.25 | 7.25 | 12.5 | 12.5 | 8.0 |
| Approx. Weight of Roll | lbs | 62 | 47 | 40 | 64 | 64/82 | 47 | 47 | 65 | 42 | 61/78 | 56 | 81 | 64 | 59 | 67 | 90 |
| 8" for 10 min | mls | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 | n/a | 0 | 0 | n/a | 0 | 0 | n/a |
| Denier of base fabric | | 840 | 600 | 600 | 600 | 600 | 450 | 600 | 600 | 300 | 600 | 300 | 300 | 300 | n/a | n/a | 300 |

*Select colors